



▶ DPF 9000 Vinyl Film

Engineering Grade Digital Print Pressure Sensitive Film

DPF 9000 is a 3.5-mil (90 microns) satin white, high-tensile, polyvinyl chloride film with medium-tack, repositionable, permanent pressure-sensitive adhesive. Designed for outdoor graphics, DPF 9000 is made of 100% polymeric face stock with a special lay-flat liner. The special adhesive system is designed to be solvent and heat resistant. DPF 9000 is designed to meet the marketing requirements and specifications of the transportation and automotive industries. The film conforms well to flat surfaces with slight contours when processed and applied according to Arlon recommendations. DPF 9000 is rated for outdoor durability up to 7 years (unprinted). Printed durability is dependent on the ink system used.

APPLICATIONS & FEATURES




- Digital printing with a wide variety of direct print systems
- Fleet markings, decorations for railway car, bus, boat, and recreational vehicle
- Gas pump skirts
- Motorcycle markings requiring Bake Cycle Curing

PERFORMANCE & PHYSICAL DATA




PROPERTY	TEST METHODS	TYPICAL VALUE
SURFACE FINISH	Gloss Meter 60° Reflection	40% to 60%
THICKNESS	Micrometer, Federal Bench Type	90 microns
TENSILE STRENGTH	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	2.3 kg/cm width
ELONGATION	Instron Tensile Tester as above	100%
SHELF LIFE	Free from excessive moisture, temperature, direct sunlight	1 year from factory shipment
APPLICATION TEMPERATURE RANGE	On clean, dry substrate	4.4°C to 38°C
SERVICE TEMPERATURE RANGE	On clean, dry substrate	-54°C to 70°C
DIMENSIONAL STABILITY	158°F (70°C), 48 hours	0.50 mm
PEEL ADHESION	PSTC-1, 15 min, RT 70°F (21°C)	0.45 kg/cm
LINER RELEASE	TLMI Release at 90°, 300 in/min (760 cm/min)	12 g/cm

Standard Terms & Conditions Apply



USA

 200 Boysenberry Lane, Placentia, CA 92870
 800 232 7161/+1 714 985 6300
 +1 714 985 6305

EUROPE

 Dr. Lelykade 22B, 2583CM Den Haag, The Netherlands
 +31 70 354 4311
 +31 70 355 7721

CHINA

 No. 1989 Xinchang Road, Weifang, Shandong, 262400
 +86 0536 6226568




TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:




All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

April 2020



USA

 200 Boysenberry Lane, Placentia, CA 92870
 800 232 7161 / +1 714 985 6300
 +1 714 985 6305

EUROPE

 Dr. Lelykade 22B, 2583CM Den Haag, The Netherlands
 +31 70 354 4311
 +31 70 355 7721

CHINA

 No. 1989 Xinchang Road, Weifang, Shandong, 262400
 +86 0536 6226568