

## Series 5000 High Gloss Calendered Vinyl Film

Series 5000: Non-Perforated - Series 5050: Perforated

Series 5000 is an ultra thin 2.8-mil (70 micron) calendered film and is one of the most pliable calendered films on the market. The product has a high gloss finish, and is ideal for signs, graphics or displays requiring vibrant color. This film is available in 37 bright colors and provides excellent cutting and weeding for improved productivity and has an outdoor durability rating of up to 6 years.

## **APPLICATIONS & FEATURES**

- Available in 37 colors
- Easy to handle 2.8-mil (70 micron) calendered film
- Cutting and weeding performance speeds up your sign production\*
- Contrasting blue liner on white makes for optimal cutting & weeding
- Recommended for flat and soft curved surfaces
- Gloss finish is excellent for banners, interior and exterior graphics
- Up to 6-years outdoor durability

## PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
SURFACE FINISH	Colors: Gloss Meter 60° Reflection	75 to 85 Gloss Units	
THICKNESS	Micrometer, Federal Bench Type	2.8-mil (70 micron)	
TENSILE STRENGTH	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	12 lb/in width	2.1 kg/cm width
ELONGATION	Instron Tensile Tester as above	≥ 150%	
SHELF LIFE	Free from excessive moisture, temperature, direct sunlight	1 year from factory shipment	
APPLICATION TEMPERATURE RANGE	On clean, dry substrate	60°F to 90°F optimum	15°C to 32°C optimum
SERVICE TEMPERATURE RANGE	Film applied to etched aluminum panels 24 hours prior to testing	-40°F to 150°F	-40°C to 65°C
HUMIDITY RESISTANCE	Film applied to etched aluminum panels 24 hours prior to testing; 100% relative humidity at 100°F (38°C) for 24 hours	No appreciable effect	
GASOLINE RESISTANCE	Film applied to etched aluminum panels 24 hours prior to testing; immersed 15 minutes at 70°F (21°C); stabilized 24 hours before inspection	No appreciable effect	
DIMENSIONAL STABILITY	158°F (70°C), 48 hours	0.025 in	0.64 mm nominal
PEEL ADHESION	PSTC-1, 15 min, RT 72°F (23°C)	≥ 40 oz/in	≥ 0.45 kg/cm
LINER RELEASE	TLMI 300 in/min (762 cm/min)	150 g/2 in	30 g/cm
			0.75 n/25 mm

Standard Terms & Conditions Apply

200 Boysenberry Lane, Placentia, CA 92870, USA

c P ±71.70.75

985 6300 **f** 

800 329 2756 +31 70 355 7721

<sup>\*</sup> For optimal weeding, font size must be 1 inch or greater

## **TERMS & CONDITIONS**

The following is made in lieu of all warranties expressed or implied:

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

a 200 Boysenberry Lane, Placentia, CA 92870, USA
b North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands
b North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands
c P +31 70 354 4311
c P +31 70 354 4311
c P +31 70 356 4311
c P +31 70 356 4311